

Technical Data Sheet

General Data

Form: Granules
Colour: Black
Filtration: 200 µm
Source: Post Consumer LDPE&LLDPE film material

Physical Properties

	Data	Ünit	Test Standarts
Ash Content	5.00 <	%	EN ISO 3451-1
MVR (190C-2.16kg)	1.09-1,15	cm ³ /10min	ISO 1133-1
Density	0.88-0.93	g/cm ³	ISO 11331
MFI (190C-2.16kg)	Between 0-1	g/10min	EN ISO 1183-1

Application

Extrusion of films

Packaging

Big Bags, weight approx. 1.150 kg

Remarks:

All tests are conducted in our laboratory, according to stated standards. The data in this technical data sheet are typical properties conforming to our current state of technical know-how and experience and are not to be construed as specification limits. Because of the variety of possible influences during processing and use of our products, they do not exempt the user from his duty to conduct own checks and tests regarding the suitability of the products. The legally binding confirmation of certain properties or of the qualification for a certain purpose cannot be derived. Possible trademark rights as well as existing laws and regulations are to be followed by the user at his own responsibility. We reserve the right to perform modifications on products.

